

## Technical Datasheet

# DUROFLOOR-PUC MF6

## Heavy-duty, self-leveling, three-component, polyurethane-cementitious screed

Description	Colors*:	red dark grey green ochre yellow black
<p>DUROFLOOR-PUC MF6 is a self-leveling, fast-setting flooring system, based on cement and polyurethane resins. It offers the following advantages:</p> <ul style="list-style-type: none"> <li>• High mechanical strength</li> <li>• Excellent chemical resistance</li> <li>• Excellent adhesion to the substrate</li> <li>• May be applied to 7-days concrete</li> <li>• Quick application</li> <li>• Very good workability and self-leveling properties</li> <li>• Broad operating temperature range</li> <li>• Odorless and non-toxic</li> <li>• Easy-to-clean</li> </ul> <p>Certified according to EN 1504-2 and classified as a coating for surface protection of concrete. CE marked. Certificate No.: 2032-CPR-10.11. Classified as a SR-B2-AR0,5-IR10 type floor coating material according to EN 13813. Certified for safe flooring applications in food handling and processing areas (ISEGA, Germany, Certification No.: 53641 U20).</p>	<p>* Coloring is possible using <b>ISOMAT DECO-COLOR</b> pigments in powder form.</p>	
<p><b>Fields of application</b></p> <p>DUROFLOOR-PUC MF6 is used in:</p> <ul style="list-style-type: none"> <li>• Food and beverage industries</li> <li>• Pharmaceutical industries</li> <li>• Professional kitchens</li> <li>• Professional refrigerators</li> <li>• Heavy-traffic floors subject to shocks</li> <li>• Areas exposed to aggressive chemical substances</li> <li>• Hospitals and labs</li> <li>• Parking spaces, etc.</li> </ul>	<p>Density of component A: 1.0 kg/l</p> <p>Density of component B: 1.21 kg/l</p> <p>Bulk density of component C: 1.5 kg/l</p> <p>Bulk density (A+B+C): 1.8 kg/l</p> <p>Mixing ratio (A:B:C): 1:1:4.8 w/w</p> <p>Pot life: ~ 20 min at +20°C</p> <p>Minimum hardening temperature: +8°C</p> <p>Water permeability: (EN 1062-3) <math>w &lt; 0.05 \text{ kg/m}^2 \text{ h}^{0.5}</math></p> <p>Foot traffic: after 8 h at +23°C</p> <p>Final strength: after 4 d at +23°C</p> <p>Compressive strength: (EN 13892-2) 48.0-52.0 N/mm<sup>2</sup></p> <p>Flexural strength: (EN 13892-2) 17.0-20.0 N/mm<sup>2</sup></p> <p>Abrasion resistance: (EN 13892-4, BCA) &lt; 50 µm, AR 0.5</p> <p>Shore D Hardness: &gt; 80.0</p> <p>Adhesion strength: (EN 1542) &gt; 3.0 N/mm<sup>2</sup> (concrete failure)</p> <p>Impact resistance: (EN ISO 6272-1) ≥ 10 Nm, IR10</p> <p>Reaction to fire (EN 13501-1): B<sub>fl</sub> - s1*</p> <p>Resistance to thermal shock: (EN 13687-5) &gt; 2,0 N/mm<sup>2</sup></p> <p>Resistance to severe chemical attack (EN 13529): Class II</p> <p>Application thickness: 3-6 mm</p>	
<p><b>Technical data</b></p> <p>Chemical base (A+B): 2-component polyurethane resin</p> <p>Chemical base C: cementitious powder</p>		

# DUROFLOOR-PUC MF6

Operating temperature range: from -40°C to +80°C, depending on the thickness of application.

\*With epoxy primer EPOXYPRIMER 500 as a system. Report No 18/17898-1886, APPLUS Laboratories – LGAI, Spain, December 2018.

## Resistance to chemical stress

DUROFLOOR-PUC MF6 is resistant to a large number of chemical stresses, such as:

- Organic acids, commonly used in the food industry: acetic acid, lactic acid, oleic acid, citric acid, etc.
- Other powerful acids, such as hydrochloric acid, sulphuric acid, etc.
- Variety of alkali, mineral oils and oil products
- Organic solvents, such as xylol, ethanol, ether, etc.

(Chemical resistance – Table 1)

In some cases of chemical stress, it is possible to see specks or discoloration on the final surface of DUROFLOOR-PUC MF6, depending on the consistency of the chemicals, the type of stress and the cleanliness of the floor. For more information, regarding the chemical resistance of DUROFLOOR-PUC MF6, contact ISOMAT Technical Support Department.

## Directions for use

### 1. Substrate

The surface to be processed must be:

- Dry and solid.
- Free from materials that might impair adhesion, such as dust, loose particles, grease, etc.
- Protected from below-surface moisture.

Moreover, the following conditions must be met:

Concrete quality: at least C20/25  
Cement screed quality: cement content 350 kg/m<sup>3</sup>  
Age: at least 7 days

Moreover, proper preparation should be ensured depending on the nature of the substrate, such as brushing, grinding, shot blasting, milling, sandblasting, water blasting, etc. Then, the surface has to be thoroughly cleaned from dust by using a high-suction vacuum cleaner.

### 2. Priming of the surface

The surface is primed using the water-based epoxy primer EPOXYPRIMER 500. On the still fresh layer quartz sand (Ø 0.3-0.8 mm) is spread. Consumption of quartz sand: approx. 3 kg/m<sup>2</sup>.

After EPOXYPRIMER 500 has hardened, any loose grains should be removed with a high-suction vacuum cleaner.

Any existing imperfections (cracks, holes) on the substrate should be filled using the epoxy stucco EPOMAX STUCCO or the epoxy paste EPOMAX-EK.

DUROFLOOR-PUC MF6 should be applied, when primer is totally dried, within 24-48 hours from its application, depending on the conditions at the jobsite. Alternatively, DUROFLOOR-PUC MF6 could be applied for priming as a scratch coat in 1mm thickness. After 24 hours, DUROFLOOR-PUC MF6 is applied on the cured scratch coat.

### Wet substrate

If the product is intended to be applied to a wet (moisture level higher than 4%) or new concrete floor (7-28 days), the surface must be primed using the two-component polyurethane primer PRIMER-PU 140. On the still fresh layer quartz sand (Ø 0.3-0.8 mm) is spread.

Consumption of quartz sand: approx. 3 kg/m<sup>2</sup>. After PRIMER-PU 140 has hardened, any loose grains should be removed with a high-suction vacuum cleaner.

### 3. Mixing method of DUROFLOOR-PUC MF6 with ISOMAT DECO-COLOR pigments

DUROFLOOR-PUC MF6 components are delivered in pre-weighed packages with fixed mixing ratio. Stir components A and B in their containers. Then, add ISOMAT DECO-COLOR pigments to component A in the right dosage (see below at **Table A**) while stirring for about 1 min using a low speed mixer (300 rpm).

# DUROFLOOR-PUC MF6

Following that, pour both components into a clean pot of about 20 l and mix for about 30-60 seconds using a low speed mixer (300 rpm). The dosage of the pigments must be kept constant in order to achieve a uniform aesthetic effect on the application surface.

Make sure to properly reach the walls and bottom of the container while stirring the components, in order to obtain a smooth mixture.

Finally, add component C and keep stirring with a low speed mixer until fully homogeneous (approx. 3-4 min). Do not add water.

## 4. Application

DUROFLOOR-PUC MF6 is applied right after mixing the components, using a notched trowel. The self-leveling layer should be rolled using a special spiked roller, to help trapped air escape. This way a bubble-free layer of uniform thickness is achieved. Applying DUROFLOOR-PUC MF6 on surfaces exposed to sun radiation does not affect the mechanical and chemical stresses of the material, but it could bring out variations in the final color (light color shades could become yellowish).

Tool cleaning:

Tools must be thoroughly cleaned with SM-28 right after use. Any hardened material can only be removed mechanically.

## Consumption

Approx. 1.8 kg/m<sup>2</sup>/mm of layer thickness.

## Packaging

DUROFLOOR-PUC MF6 is available in 34 kg packaging (A+B+C) in the following mixing ratios:

Component A:	5 kg
Component B:	5 kg
Component C:	24 kg

## Shel life – Storage

12 months from production date in sealed packaging, stored in cool and dry conditions.

## Remarks

- The processing time of DUROFLOOR-PUC MF6 is significantly affected by ambient temperature. The ideal temperature of application is between +15°C and +20°C, in order to ensure optimal workability and curing time. Low room temperature (<+15°C) will delay the curing time, while at higher temperatures (>+20°C), curing takes place much faster. It is recommended to mildly preheat the materials during winter, and to store them in a cool room before use in the summer. Especially for component A (isocyanate), exposure to temperatures below 5°C during transport or storage can cause increase of the viscosity or even crystallization (in case of extremely low temperatures), depending on the time of the exposure and the minimum temperature at which the material was exposed. The process is reversible (by storing the material at room temperature and waiting for the viscosity to return to normal before application) and does not affect the properties and performance of the material.
- Before applying the material on cementitious substrates, contraction-expansion joints should be placed at every 25 m<sup>2</sup> and filled with proper elastic materials after the end of the application.
- After application, the fresh surface of DUROFLOOR-PUC MF6 must be protected for about 4-6 hours (depending on the weather conditions) from moisture, as it may adversely affect the final finishing of the material and disrupt the hardening.
- Do not mix DUROFLOOR-PUC MF6 with other binding materials (e.g. cement, gypsum, lime) or other additives, such as solvents.
- Do not use the mix that has already begun to set in the mixing tank.
- DUROFLOOR-PUC MF6 is not applied on metal surfaces, tile surfaces, wooden or asphalt substrates and lightweight concrete.
- After hardening, DUROFLOOR-PUC MF6 is totally harmless.
- Please consult the safety instructions written on the packaging before use.
- DUROFLOOR-PUC MF6 is intended for professional use only.

# DUROFLOOR-PUC MF6

---

## Volatile Organic Compounds (VOCs)

According to Directive 2004/42/CE (Annex II, table A), the maximum allowed VOC content for the product subcategory j, type WB is 140 g/l (2010) for the ready-to-use product.

The ready-to-use product DUROFLOOR-PUC MF6 contains a maximum content of 140 g/l VOC.

## **Mixing ratio of ISOMAT DECO-COLOR per 34 kg DUROFLOOR-PUC MF6**

**TABLE A**

Red	4 B	4 x 50 g red-brown ISOMAT DECO-COLOR
Dark Grey	1 C	1 x 50 g black ISOMAT DECO-COLOR
Green	4 F	4 x 50 g green ISOMAT DECO-COLOR
Ochre	4 E	4 x 50 g ochre ISOMAT DECO-COLOR
Yellow	0.5 E	25 g ochre ISOMAT DECO-COLOR
Black	4 C	4 x 50 g black ISOMAT DECO-COLOR

# DUROFLOOR-PUC MF6

## CHEMICAL RESISTANCE DUROFLOOR-PUC MF6

**TABLE 1**

Chemical Compound	Observations after 28 days exposure
Hydrochloric acid (37% w/w)	Slight discoloration
Nitric acid (40% w/w)	Intense discoloration
Lactic acid (90% w/w)	No effect noticed
Xylene (100% w/w)	No effect noticed
Acetic acid (30% w/w)	Slight discoloration
Sulfuric acid (50% w/w)	No effect noticed
Oleic acid (50% w/w)	No effect noticed
Citric acid (30% w/w)	No effect noticed

**TABLE ACCORDING TO EN 1504-2 (CLASS II)**


Test group (EN 13529)	Description	Observations after 28 days exposure
1	Petrol	No blistering, flaking or cracking after 28 days. Slight discoloration
2	Aviation fuel	No blistering, flaking or cracking after 28 days. Slight discoloration
4	All hydrocarbons incl. group 2 and 3 except 4 a and 4 b and used motor and gear oils	No blistering, flaking or cracking after 28 days. Slight discoloration
4a	Benzene and benzene containing mixtures (incl. 2 – 4 b)	No blistering, flaking or cracking after 28 days. Slight discoloration
5	Mono- and polyalcohols (up to 48 Vol.-% methanol), glycol ethers	No blistering, flaking or cracking after 28 days. Slight discoloration
5a	All alcohols and glycol ethers (incl. 5)	No blistering, flaking or cracking after 28 days. Slight discoloration


# DUROFLOOR-PUC MF6

<b>6</b>	Halogenated hydrocarbons (incl. 6 b)	No blistering, flaking or cracking after 28 days. Slight discoloration
<b>6a</b>	All aliphatic halogenated hydrocarbons (incl. 6 and 6 b)	No blistering, flaking or cracking after 28 days. Slight discoloration
<b>6b</b>	Aromatic halogenated hydrocarbons	No blistering, flaking or cracking after 28 days. Slight discoloration
<b>7</b>	All organic esters and ketones (incl. 7 a)	No blistering, flaking or cracking after 28 days. Slight discoloration
<b>8</b>	Aliphatic aldehydes	No blistering, flaking or cracking after 28 days. Slight discoloration
<b>9</b>	Aqueous solutions of organic acids up to 10 %	No blistering, flaking or cracking after 28 days. Slight discoloration
<b>9a</b>	Organic acids (except formic acid) and their salts (in aqueous solution)	Slight blistering and discoloration
<b>10</b>	Inorganic acids up to 20 % and acidic hydrolysing salts in aqueous solution (pH < 6) except hydrofluoric acid and oxidizing acids and their salts	No blistering, flaking or cracking after 28 days. Slight discoloration
<b>11</b>	Inorganic bases and their alkaline hydrolysing salts in aqueous solution (pH > 8) except solutions of ammonium and oxidizing solutions of salts (e. g. hypochloride)	No blistering, flaking or cracking after 28 days. Slight discoloration
<b>12</b>	Solutions of inorganic non-oxidizing salts showing a pH = 6 – 8	No blistering, flaking or cracking after 28 days. Slight discoloration
<b>13</b>	Amines and their salts (in aqueous solution)	Blistering and softening followed by destruction of coating
<b>15</b>	Cyclic and acyclic ethers	Flaking and discoloration
<b>15a</b>	Acyclic ethers	No blistering, flaking or cracking after 28 days. Slight discoloration



# DUROFLOOR-PUC MF6


<b>ISOMAT S.A.</b> 17 <sup>th</sup> km Thessaloniki – Ag. Athanasios P.O. BOX 1043, 570 03 Ag. Athanasios, Greece
<b>18</b>
<p style="text-align: center;"><b>EN 13813 SR-B2,0-AR0,5-IR10</b></p> <p>DoP No.: DUROFLOOR PUC MF6 /1281-01</p> <p>Synthetic resin screed material for use internally in buildings</p> <p>Reaction to fire: B<sub>fl</sub> - s1</p> <p>Release of corrosive substances: SR</p> <p>Water permeability: NPD</p> <p>Wear resistance: AR0,5</p> <p>Bond strength: B2</p> <p>Impact resistance: IR10</p> <p>Sound insulation: NPD</p> <p>Sound absorption: NPD</p> <p>Thermal resistance: NPD</p> <p>Chemical resistance: NPD</p>


<b>2032</b>
<b>ISOMAT S.A.</b> 17 <sup>th</sup> km Thessaloniki – Ag. Athanasios P.O. BOX 1043, 570 03 Ag. Athanasios, Greece
<b>18</b>
<p style="text-align: center;">2032-CPR-10.11</p> <p>DoP No.: DUROFLOOR-PUC MF6 / 1283-01</p> <p style="text-align: center;"><b>EN 1504-2</b></p> <p style="text-align: center;">Surface protection products</p> <p style="text-align: center;">Coating</p> <p>Permeability to CO<sub>2</sub>: Sd &gt; 50m</p> <p>Water vapor permeability: Class I (permeable)</p> <p>Abrasion resistance: AR 0.5</p> <p>Impact resistance: Class II</p> <p>Resistance to severe chemical attack: Class II</p> <p>Resistance to thermal shock: <math>\geq 2.0 \text{ N/mm}^2</math></p> <p>Capillary absorption: <math>w &lt; 0.1 \text{ kg/m}^2 \cdot \text{h}^{0.5}</math></p> <p>Adhesion: <math>\geq 2.0 \text{ N/mm}^2</math></p> <p>Reaction to fire: B<sub>fl</sub> - s1</p> <p>Dangerous substances comply with 5.3</p>

**ISOMAT S.A.**  
BUILDING CHEMICALS AND MORTARS  
**MAIN OFFICES - FACTORY:**  
17<sup>th</sup> km Thessaloniki – Ag. Athanasios Road,  
P.O. BOX 1043, 570 03 Ag. Athanasios, Greece,  
Tel.: +30 2310 576 000, Fax: 22620 31 644  
[www.isomat.eu](http://www.isomat.eu) e-mail: [support@isomat.eu](mailto:support@isomat.eu)